

**AHI Supply, LP**  
**PO Box 2789**  
**Alvin, Texas 77512**  
**Tel 281-331-0088 Fax 281-331-9813**  
**www.ahi-supply.com**



**Spectrum Cement Division**

**To:** \_\_\_\_\_ **Date:** \_\_\_\_\_

**Attention:** \_\_\_\_\_

**From:** \_\_\_\_\_

**Subject:** Submittal for approval

**Project:** \_\_\_\_\_

**Spectrum Portland & Lime Cement (Type N) \***

**Product information:**

This Portland Cement & Lime Cement is manufactured by our Spectrum Cement Division of Buda, Texas. There are several colors available (*see below*) of this product which is a Portland Cement and Lime Mortar Proportion Mortar Mix <sup>1</sup>, representing the cementitious component of an ASTM C 270-00 mortar. Each 70 pound bag of this cement is to be mixed with masonry sand meeting ASTM C144 at a ratio of no less than 2¼ & no more than 3 times the volume of the cementitious material<sup>2</sup>.

**AHI suggests that the project Engineer and/or Architect, masonry contractor and all other appropriate parties review this product & submittal and determine its acceptability prior to the initiation of the project.** AHI asserts that the materials and blending of Spectrum Portland & Lime Cement (Type N) are proper: that said please note that sand is added to our product by the masonry contractor on the jobsite.

Should you require information on the ASTM Specifications controlling our product, samples of our product, Material Safety Data Sheets, references or if we may be of service to you in any way, please contact us.

***\*Applies to the following Gray, White & Colored Cements:***  
***Gray, White, Stone Buff, Almond, Eldridge Buff, Texas Gold, Pan Am Red,***  
***UT Tan and Brazos Brown***

**Thank you for the opportunity of furnishing our product**  
**on this important project!**

---

<sup>1</sup> The Portland Cement conforms to ASTM C 150 Type I. The hydrated lime used in this product conforms to ASTM C207.

<sup>2</sup> Each 70-pound bag of this colored Portland and Lime Cement (Type N) is a blend of the equivalent by weight of 1 bag of Type I Portland Cement and 1 bag of Hydrated lime. This mix proportion is typical of a field mixed mortar.