



TEXAS - LEHIGH CEMENT COMPANY

P.O. Box 610 Buda, Texas 78610 (512) 295-6111



LABORATORY TEST REPORT

Consignee: _____ Address _____

Date: Monthly Average for December, 2009 Plant _____

Type S Masonry Car/Truck _____ Bin No. 3 Quantity _____

RESULT OF TESTS

| | | |
|---------------|---|------|
| Remarks _____ | -325 sieve(%) ASTM C 430_____ | 95.9 |
| _____ | Autoclave Exp.(%)-ASTM C151__ | 0.01 |
| _____ | Time of Set (Vicat)-ASTM C 191 | |
| _____ | Initial (Minutes)_____ | 163 |
| _____ | Final (Minutes)_____ | 369 |
| _____ | Air Content (%) ASTM C185_____ | 14 |
| _____ | H2O Retention (%) ASTM C 91__ | 84 |
| | Compressive Strength, PSI (ASTM C 109 Mortar Cubes): | |
| | 7 - Day_____ | 2070 |
| | 28 - Day__ | 2670 |

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of the current applicable specification ASTM C91. The above data represents the average of representative samples from production. We are not responsible for improper use or workmanship.

Date: **January 11, 2010**

QC Manager

Jim Jarl